

Silicone's, Inc. Dist. by: ANCHOR-SEAL 10/21/09
Product # GI-179A Teal Activator for GI-RTV

Features:

Increases the tensile strength
Increases elongation
Decreases hardness in 25A
or less products
Maximum stretch

Applications:

RTV molds
Fabricating parts
Glove molds
Vacuum molds
Block molds

Mixing & Curing Instructions:

100 Parts Base to 10 Parts Activator by wt.

Working Time, hours 1-1.5
Cure Time, hours 18-24

Properties:

Shore A Hardness..... standard data sheet less 2
Tensile Strength standard data sheet plus 100 psi
Elongation standard data sheet plus 100%
Cure against clay..... excellent
Color teal
Shelf Life, unopened containers 6 months

-more-

Silicone's, Inc. Dist. by: ANCHOR-SEAL
Product # GI-179A Teal Activator for GI-RTV

IMPORTANT INFORMATION: READ BEFORE USING PRODUCT

Directions for Use: Because of differences in density, *pigments and fillers, when present, may separate* from the liquid components during storage. To insure product homogeneity and maximum performance, check the containers for settling. Loosen any settled pigments from the bottom of the container and ***thoroughly mix contents prior to use.*** Use a mixing stick or power mix at slow speed with a drill press and dispersion blade.

Measuring: Carefully weigh Part B and Part A components with an accurate scale. If measuring volumetrically, use precise metering pumps, graduated/pre-marked containers or pre-measured kits. Place the correct proportions of Part B and Part A into a straight-sided container. **Note:** Altering the mix ratio from what is specified on the data sheet is not recommended. Cured properties could be adversely affected.

Mixing: Mix thoroughly with a flat-ended stick or a slow speed drill press with a dispersion blade. Scrape the sides and bottom occasionally to assure a thorough blend. Do not whip excessive air into the mixture. To guard against partially cured sections, never apply material *scraped* from the sides of the original mixing container. For best results, transfer the mixture into a second container and stir it again before application. This will help insure consistent properties and maximum performance.

De-airing: Some applications require a totally air-free product. If a vacuum pump and chamber are used, evacuate the material for 10-15 minutes @ 28-29 inches of mercury. Allow sufficient space above the liquid for expansion, about four times the liquid volume. Curing under pressure, 60 psi will compress most bubbles and promote a bubble free casting.

Curing: A tin based RTV will cure against all surfaces without fear of inhibition caused by chemical contamination. Proper curing requires exposure to a minimum 50% relative humidity. Do not try to cure the product in a completely closed cavity unless a few % of U.F.C. (ultra fast catalyst) is added to the mixture.

Handling Cautions: Review the Material Safety Data Sheet before using this product.

Warning: For Industrial Use Only. All chemicals must be handled with care. Avoid breathing fumes and mists, they could cause respiratory discomfort or damage. Work in a well-ventilated area. Avoid all contact with the skin. If contact occurs, wash affected area thoroughly with soap and water. Repeated skin contact may cause dermatitis in susceptible individuals. Wear protective clothing and gloves. Irritation may result if this product is splashed into the eyes. Always wear eye protection. If eye contact occurs, flood eyes with clear water for 15 minutes and immediately seek medical attention. Always maintain good industrial hygiene when using this product.

Notice To Buyer: All information contained herein is believed to be accurate. However, it is the responsibility of the end user to determine the suitability of this product in his particular application. As the use of this product by others is beyond our control no warranty, whether expressed or implied is made by Anchor-Seal, Inc. or any of its representatives as to this product's merchantability or fitness for a particular purpose. Under no circumstances shall Anchor-Seal, Inc. be liable for incidental, consequential or other damages for any reason. The sole liability of Anchor-Seal, Inc. shall be to refund the purchase price or replace materials deemed to be defective by us.